

TRGOVIR-Bitumin N

PRODUCT DATA SHEET

3.10.2017

USE

BITUMIN N is applied in subterranean and above-ground waterproofing systems in combination with bituminous membranes or as a self-contained waterproofing layer, if it meets the requirements of the intended application site.

MOUNTING

It is recommended to treat the BITUMIN N surface with a layer of Trgovir Prajmer before application. Apply hot BITUMIN N (temperature approx. 170 ° C) to the dry layer of the Trgovir Prajmer. The mass consumption is 1.5 - 2 kg / m².

FEATURES	TEST PROCEDURE	UNIT	DECLARED VALUE	TOLERANCE	
				Lower limit	Upper limit
Proportion of Bitumen	U.M8.085	% (m/m)	100	100	100
Point of softening by method RING-KUGEL *	U.M8.085	%	≥80	0	0
Proprtion of filler	U.M8.085	°C	0	0	0
Cold resistance	U.M8.085	°C	≤70	/	/
Heat resistance	U.M8.085	°C	≤0	/	/
Settling in the heated state (180 ° C)	U.M8.085	% (m/m)	0	/	/

STORAGE

BITUMIN N is packed in tin cans in a quantity of 23 kg (smaller weight deviations are possible). It is stored in a covered area, protected from the sun, heat, open flames and mechanical damage of the packaging.

PACKAGING

The goods must be transported in an upright position and secured against tipping over. In addition, the goods must be protected from extreme weather conditions.

PERIOD OF USE

/