

TRGOVIR-Prajmer

PRODUCT DATA SHEET

3.10.2017

USE

Waterproof bituminous coating with organic solvent for a cold process based on distilled bitumen. Resistant to low and elevated temperature, water and diluted acid.

MOUNTING

Cold with a brush or roller at (min. temp. 5 ° C). The surface must be clean and dry.

FEATURES	TEST PROCEDURE	UNIT	DECLARED VALUE	TOLERANCE	
				Lower limit	Upper limit
Proportion of Bitumen *	DIN 53215	%m/m	66/71	-10%	+10%
Point of softening by method RING-KUGEL *	HRN EN 1427	°C	≥40 / 42	/	/
Flash Point (COC)*	HRN ISO 2592	°C	≥35 / 58	/	/
Drying Time (Room Temperature)	/	H	3-6 / 6	/	/
Density at 20 ° C	/	g/cm ³	0,930 / 0,950	-5%	+5%
Viscosity (Ford Ø 4mm)	/	sec	90 / 105	-20%	+20%
Consumption	/	l/m ²	0,3 – 0,5	/	/

* Properties analyzed at the Institute of Civil Engineering IGH Zagreb - Croatia

PRECAUTIONS:

When working indoors, ensure good ventilation. Due to the flammability is forbidden any use of an open flame or sparkling tools in the vicinity.

STORAGE

In a covered area. Protect it from sun, heat, open flames and mechanical damage.

PACKAGING

TRGOVIR Primer is packaged in plastic canisters of 5 or 10 liters and, on customer request, in larger containers (drums, tanks, etc.) as well.

TRANSPORT

In an upright position, secured by overturning due to external influences. Goods must be protected from extreme weather conditions.

PERIOD OF USE

/